

## CLAIMS

1. A method of molding an elastomeric article comprising  
putting an elastomeric article in a mold,  
softening the elastomeric article in the mold by heating  
the elastomeric article,  
pressing the elastomeric article against the mold by  
pressurizing an inside of the elastomeric article by letting a  
fluid therein, and  
changing the pressure of said fluid in a short cycle so as  
to beat the elastomeric article against the mold.
2. The method according to claim 1, wherein  
one cycle of the change in the pressure comprises  
a decrease of short duration of not more than 60 seconds and  
an increase of short duration of not more than 60 seconds.
3. The method according to claim 1, wherein  
the number of cycles of the change in the pressure is at  
least two
4. The method according to claim 1, wherein  
the number of cycles of the change in the pressure is at  
least two but at most fifty.
5. The method according to claim 1, wherein  
the number of cycles of the change in the pressure is at  
least two but at most twenty.
6. The method according to claim 1, wherein  
the number of cycles of the change in the pressure is at  
least two but at most ten.
7. The method according to claim 1, wherein  
said elastomeric article is a pneumatic tire.
8. The method according to claim 7, wherein

one cycle of the change in the pressure comprises a decrease of short duration of not more than 10 seconds and an increase of short duration of not more than 10 seconds.

9. The method according to claim 1, wherein

said fluid is a heating medium which is let in the inside of the elastomeric article to heat the elastomeric article.

10. The method according to claim 1, wherein

said fluid is a heating medium which is let in the inside of the elastomeric article to heat the elastomeric article, and thereafter a pressurizing medium is let in the inside of the elastomeric article to press the elastomeric article against the mold.

11. The method according to claim 10, wherein

the heating medium is a gas having a high heat capacity, and the pressurizing medium is an inert gas having a heat capacity lower than the heat capacity of the heating medium.

12. The method according to claim 9 or 10, wherein

in the process of heating the elastomeric article by the heating medium, after the cyclic change in the pressure of the heating medium is made, the pressure is kept substantially constant for a certain length of time.